

ELECTRODES STELLORIC BASE FER

ALLIAGES BASE FER		ANALYSE TYPE									
Nuance	Dureté HRc	C%	Si%	Cr%	Mo%	Mn%	W%	B%	Fe%	Co%	Autres%
E A	60/63	04-juin	0,5	34-36	-	0,2	-	-	Bal	-	-
331	54/58	4	1	25	6	-	-	-	Bal	-	1